## **AWTA PRODUCT TESTING**

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Client: Intrepid Carpet Tiles Pty Ltd

> 14 Carsten Road Gepps Cross SA 5094

18-007483 Test Number : **Issue Date** 13/03/2019

**Print Date** 13/03/2019

"Tetris/serenity/ Uptown/ Expression" **Sample Description** Clients Ref:

> Colour: Various Flooring End Use:

100% Solution Dyed Nylon Nominal Composition: 600 g/m2 Nominal Mass per Unit Area/Density:

Nominal Thickness: total 7mm

AS/ISO 9239.1-2003 Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a

**Radiant Heat Source** 

Date of Sample Arrival 14/12/2018 **Date Tested** 12/03/2019

| CHF Value   | 1   | 2   | 3   | Mean |       |
|-------------|-----|-----|-----|------|-------|
| Length      | 3.0 | 3.2 | 3.4 | 3.2  | kW/m² |
| Width       | 8.6 | -   | -   | -    | kW/m² |
|             |     |     |     |      |       |
| HF-30 Value | 1   | 2   | 3   | Mean |       |
| Length      | 3.0 | 3.2 | 3.4 | 3.2  | kW/m² |
| Width       | -   | -   | -   | -    | kW/m² |
|             |     |     |     |      |       |
| Smoke Value | 1   | 2   | 3   | Mean |       |
| Length      | 288 | 231 | 247 | 255  | %.min |
| Width       | 123 | -   | -   | -    | %.min |
|             |     |     |     |      |       |

Melting Yes

159216 33034 Page 1 of 2

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing

Mechanical Testing

Performance & Approvals Testing

: Accreditation No Accreditation No

: Accreditation No 1356

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA



Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

A. JACKSON B.Sc.(Hons)

## **AWTA Product Testing**

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Client: Intrepid Carpet Tiles Pty Ltd

> 14 Carsten Road Gepps Cross SA 5094

18-007483 Test Number : **Issue Date** 

13/03/2019

**Print Date** 13/03/2019

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

159216 33034

Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing

Mechanical Testing


the Managing Director of AWTA Ltd.

Performance & Approvals Testing

: Accreditation No

Accreditation No

· Accreditation No. 1356



APPROVED SIGNATORY



A. JACKSON B.Sc.(Hons)

Page 2 of 2

983

Australian Wool testing Authority Ltd Copyright - All Rights Reserved